totalElement


SPECIFICATION SHEET
Part no. B60X15X10MMN52

# Bar Magnet

## 60 x 15 x 10 mm (2.3622 x 0.5906 x 0.3937 Inch)


Width x Length x Thickness

ISOMETRIC VIEW — Not to scale



| SPECIFICATIONS | |
|---|---|
| WIDTH | 60.00 mm [2.3622 Inch] |
| LENGTH | 15.00 mm [0.5906 Inch] |
| THICKNESS | 10.00 mm [0.3937 Inch] |
| TOLERANCE | ±0.10 mm [±0.004 Inch] |
| MATERIAL | Sintered Neodymium (NdFeB) |
| GRADE | N52 |
| COATING | Nickel-Copper-Nickel (Ni-Cu-Ni) |
| MAGNETIZATION | Through the thickness |
| PULL FORCE | 66.5 lbs (30.2 kg) |
| SURFACE FIELD | 4,547 Gauss (455 mT) |
| WEIGHT (EACH) | 68.4 g (2.41 oz) |

DIMENSIONS mm [Inch] · not to scale




MAGNETIZATION




Magnetized through the 10.00 [0.3937] dimension. Pole faces shown for illustration.

GRADE PROPERTIES · N52

| PROPERTY | SI | CGS / IMPERIAL |
|---|---|---|
| Remanence (Br) | 1.43–1.48 T | 14.3–14.8 kG |
| Coercivity (Hcb) | ≥ 836 kA/m | ≥ 10.5 kOe |
| Intrinsic coercivity (Hcj) | ≥ 876 kA/m | ≥ 11 kOe |
| Max. energy product (BH)max | 398–422 kJ/m³ | 50–53 MGOe |
| Max. operating temperature | 80 °C | 176 °F |

Typical values for sintered NdFeB of grade N52 at room temperature, not measured on this part. The highest safe working temperature also depends on the magnet's shape and how it's used.

Handling: neodymium magnets are brittle and can chip, or pinch skin, if they snap together. Keep them away from pacemakers and magnetic media.

VIEW ONLINE

Scan to open this magnet on totalElement.com.

CAD FILES

The technical drawing and 3D model are on the product page.

totalElement
totalElement.com
help@totalelement.com
1 (855) 328-2822