totalElement


SPECIFICATION SHEET
Part no. BCS1X12X14N52

Double Countersunk Block Magnet

1 x 1/2 x 1/4 Inch (25.40 x 12.70 x 6.35 mm)


Width x Length x Thickness

ISOMETRIC VIEW — Not to scale




SPECIFICATIONS	
WIDTH	1.000 Inch [25.40 mm]
LENGTH	0.500 Inch [12.70 mm]
THICKNESS	0.250 Inch [6.35 mm]
TOLERANCE	±0.004 Inch [±0.10 mm]
MATERIAL	Sintered Neodymium (NdFeB)
GRADE	N52
COATING	Nickel-Copper-Nickel (Ni-Cu-Ni)
MAGNETIZATION	Through the thickness
COUNTERSINK	Ø0.295 [7.49] × 82°
COUNTERSUNK SIDE	Both sides
THROUGH HOLE	Ø0.170 [4.32], 2 holes 0.500 [12.70] apart
SCREW	#6 flat head
PULL FORCE	18.8 lbs (8.5 kg)

DIMENSIONS — Inch [mm] · not to scale



TOP VIEW



FRONT VIEW

MAGNETIZATION



Magnetized through the 0.250 [6.35] dimension. Countersunk on both faces. Pole faces shown for illustration.

GRADE PROPERTIES · N52

PROPERTY	SI	CGS / IMPERIAL
Remanence (Br)	1.43–1.48 T	14.3–14.8 kG
Coercivity (Hcb)	≥ 836 kA/m	≥ 10.5 kOe
Intrinsic coercivity (Hcj)	≥ 876 kA/m	≥ 11 kOe
Max. energy product (BH)max	398–422 kJ/m³	50–53 MGOe
Max. operating temperature	80 °C	176 °F

Typical values for sintered NdFeB of grade N52 at room temperature, not measured on this part. The highest safe working temperature also depends on the magnet's shape and how it's used.

Handling: neodymium magnets are brittle and can chip, or pinch skin, if they snap together. Keep them away from pacemakers and magnetic media.

VIEW ONLINE

Scan to open this magnet on totalElement.com.

CAD FILES

The technical drawing and 3D model are on the product page.

totalElement
totalElement.com
help@totalelement.com
1 (855) 328-2822